

GALVEX 20.02

Universal detergent for the removal of polishing pastes, soluble oil and light pollutions in ultrasonic process.

LUXURY ACCESSORIES RANGE

FUNCTION	APPLICATION/POLLUTION
Ultrasonic cleaning, interoperation, surface preparation	Soluble oils, polishing pastes, tumbling residues, etc.

COMPATIBILITY

- Stainless steel
- Brass (leaded and unleaded)
- Rhodium, palladium
- Gold: white, pink, yellow
- ABS
- Aluminium
- Nickel silver

COMPONENTS

- Surfactants, solubilising agent
- No NTA, phosphates, DEA
- No CMR compound, REACH compliant

PHYSICOCHEMICAL DATA

■ pH concentrated: 10

■ Density: 1.03

Surface tension: 27.6 mN/m

INSTRUCTIONS FOR USE*

Concentration: 2 to 5%Temperature: 40 to 70°C

■ Time: 3 to 5 minutes

Surfactants Cavitation bubbles Substrate Parameters for cleaning: To % Time US Clean and bright surface. Cleaned blind holes.

STORAGE CONDITIONS

- Keep the recipient hermetically sealed between 5°C and 40°C (41°F and 104°F) in a dry place.
- Always keep in packaging made from the same material as the original packaging (HDPE).

PROCESS EXAMPLES

Cleaning after polishing

CLEANING



• Final cleaning and brightening

CLEANING

GALVEX 20.02	
Conc.: 2-5%	_
Temp.: 40-7 104 Time: 3-5	-158°F
US	

TAP WATER RINSE

Temp.: 20-30°C 68-86°F Time: 2-3 min RODASTEL 30

Tap water
Conc.: 3-5%
Temp.: 30-60°C
86-440°F
Time: 2-3 min
US

TAP WATER RINSE

Temp.: 20-30°C 68-86°F Time: 1-2 min DI WATER RINSE

Temp.: 20-30°C 68-86°F Time: 1-2 min

DI WATER RINSE

Temp.: 20-30°C
68-86°F

Time: 1-2 min

HOT AIR DRYING

Application Centre

If you have any questions, please contact our Application Centre on: +41 22 365 46 66





^{*}Dependent on the quality of the water and the nature and quantity of contaminants.